

Technical Information

DIRECTFILLER BLACK, GREY and WHITE

Applications

A 1.6.5

Process description

Presentation of possible applications for DIRECTFILLER


Substrates

- Steel, galvanized steel, aluminum, old paintwork, GRP / SMC
- PU-RIM, PP-EPDM, ABS, GRP / SMC, PC-PBTP, PA, PPO, rigid PVC

Products required

- DIRECTFILLER GREY, BLACK and WHITE

Primer

	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER GREY D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 20% by vol. 20% by vol.
--	--	---	--

Primer Filler

	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER GREY D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 20% by vol. 20% by vol.
---	--	---	--

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.mppaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 10/2015




Technical Information


DIRECTFILLER BLACK, GREY and WHITE

Applications

A 1.6.5


Primer Filler


	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER BLACK D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 20% by vol. 20% by vol.
---	--	--	--

	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER WHITE D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 20% by vol. 20% by vol.
---	--	--	--

Primer Filler High-build version

	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER GREY D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 20% by vol. 20% by vol.
--	--	---	--

	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER BLACK D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 20% by vol. 20% by vol.
---	--	--	--

	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER WHITE D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 20% by vol. 20% by vol.
---	--	--	--

Technical Information


DIRECTFILLER BLACK, GREY and WHITE


Applications

A 1.6.5

Wet – on – wet Filler

	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER GREY D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 25% by vol. 25% by vol.
---	--	---	--


	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER BLACK D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 25% by vol. 25% by vol.
---	--	--	--

	Steel, galvanized steel, aluminum, old paintwork GRP / SMC	DIRECTFILLER WHITE D 701 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 25% by vol. 25% by vol.
---	--	--	--

Wet – on – wet Filler application on plastic substrates

	PU-RIM, PP-EPDM, ABS, GRP / SMC, PC-PBTP, PA, PPO, rigid PVC	DIRECTFILLER GREY D 701 FLEXPRO	100% by vol. 25% by vol. 25% by vol.
---	--	---------------------------------------	--

	PU-RIM, PP-EPDM, ABS, GRP / SMC, PC-PBTP, PA, PPO, rigid PVC	DIRECTFILLER BLACK D 701 FLEXPRO	100% by vol. 25% by vol. 25% by vol.
---	--	--	--

	PU-RIM, PP-EPDM, ABS, GRP / SMC, PC-PBTP, PA, PPO, rigid PVC	DIRECTFILLER WHITE D 701 FLEXPRO	100% by vol. 25% by vol. 25% by vol.
---	--	--	--

Safety instructions

It cannot be ruled out that these products contain particles < 0.1 µm.

The products are suitable for professional use only.

For the use of these products please adhere to the actual safety recommendations and the personal protective equipment.