

Technical Information

PK 600



Cleaner plastics

Product Category: **C 1**

Fields of use

Solvent borne universal cleaner for plastics, specifically suited to remove the release agents used in manufacturing of plastic parts, especially for preparation of new bumpers before refinishing.

PK 600 is recommended for the use of new automotive plastic add-on parts, all common plastic substrates, plastics PU foam and polyamide and GRP / SMC

Additional Information

Technical characteristics

Solids content /	Density PK 600: 0.788 g/cm ³
Storage temperature min. 5°C up to max. 45°C	Shelf life 36 months

Application

PK 600 is ready for use.

Substrate / Pre-treatment / Cleaning

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.mppaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 03/2018



PK 600



Soak a clean and dry lint-free cloth with PK 600.
Clean small areas of approx. 0.5 m² of the surface to be painted and wipe these areas immediately afterwards with a dry cloth of the same quality.
PK 600 should not dry on the surface being treated.

Attention:

Individual paint coats may suffer surface etching from the use of PK 600. In this case, ensure a good flash-off of the substrate before going on with the repair so that no solvents will be trapped in the new paint system. In extreme cases, remove the affected paint coats before applying the new paint system.

Finishing

As specified in the R-M PREP'ART processes A 1.5 and A 1.6

Safety instructions

PK 600: 2004/42/IIIB(a)(850)793: The EU limit value for this product (product category: IIB.a) in ready-for-use form is max 850 grams of VOC per liter. The VOC content of this product is 793 g/l.