



Additive to accelerate drying

Product Category: **C 5**

Fields of use

Additive to accelerate drying of R-M 2-component standard VOC clears and R-M 2-component standard clears on vertical surfaces.

Additional Information

The additive can also be used to reduce the drying times of PERFECTFILLER. SPEEDFLASH increases the chemical reactivity of the products in which it is used, allowing shorter waiting times before sanding, polishing operations or reassembly can be started. SPEEDFLASH S is particularly suitable for small repairs.

Technical characteristics

Solids content < 0.5 %	Density 0.830– 0.930 g/cm ³
Storage temperature min. 5°C to max. 45°C	Shelf life 36 months

Application

The amount of SPEEDFLASH to be added corresponds with the amount of thinner indicated in the standard mixing ratio.

Substrate / Pre-treatment / Cleaning


As specified in the technical data sheet of the product in which SPEEDFLASH is being used.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.mpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 12/2014



SPEEDFLASH



	R-M standard-VOC-clear 300% by vol. H 420 100% by vol. SPEEDFLASH 100% by vol. Mix well and strain before application.	R-M standard-clear 100% by vol. H 9000 25% by vol. SPEEDFLASH 25% by vol. Mix well and strain before application.
	PERFECTFILLER 100% by vol. D 70 / D 80 25% by vol. SPEEDFLASH 25% by vol. Mix well and strain before application.	
The use of SPEEDFLASH will reduce the potlife of the products.		
	As specified in the technical data sheet of the product in which SPEEDFLASH is being used.	
	As specified in the technical data sheet of the product in which SPEEDFLASH is being used.	
	CHRONOLUX CP 50°C: 15 min. 60°C: 10 min.	
	CRYSTALCLEAR CP / DIAMONTCLEAR CP / STARLUX CP 30 min. 25 min.	
	CHRONOTOP 10 min. /	
	CRYSTALTOP HS / STARTOP HS 15 min. 10 min.	
	PERFECTFILLER WHITE / GREY / BLACK 20°C: 2 h 60°C: 15 min.	

Finishing

Safety instructions

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.