

# BrushBODY

## B 2A13

### Multibrushing body filler

<b>Application:</b>	Advance Series - undercoat solutions.
<b>Key Features:</b>	Coarse and fine body filler - brushing. For modelling of profiles and contours.
<b>Remarks:</b>	Stir well before use. Mix intensively to avoid any marbling effect.

---

<b>Storage temperature</b>	5-45 °C
<b>Shelf life</b>	12 months

---



#### Cleaning

Clean with PK 1A15 or PK 2A15.

---

#### Handling

##### Product suitable on



- Sheet steel
- Aluminium
- OEM parts with e-coat
- Old paintwork



2 - 3 x

---

#### Safety advice:

**2004/42/IIIB(b)(250)180:** The EU limit value for this product (product category: IIB.b) in ready-for-use form is max 250 grams of VOC per liter. The VOC content of this product is 180 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of these products please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# BrushBODY

## B 2A13

### Multibrushing body filler



#### Mixing Ratio

B 2A13 Multibrushing body filler  
100% by weight



#### Hardener

H 2RM1 Body filler hardener  
2-3% by weight



#### Thinner

R 2A14 Thinner, fast  
up to max. 4%

Potlife at 20°C      5 min

---

#### Drying



Drying at 20°C      30 min



Infrared (short wave)      5-7 min



#### Orbital sanding, dry

P80 / P150 / P240 (use Guide Coat)

---

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

#### Safety advice:

**2004/42/IIIB(b)(250)180:** The EU limit value for this product (product category: IIB.b) in ready-for-use form is max 250 grams of VOC per liter. The VOC content of this product is 180 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of these products please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.