

FastTOP

C 2A44

Variant with flex additive A 2A44 FlexADD

Application:	Advance Series - Clear coat, fast drying C 2A44 FastTOP with flex additive A 2A44 FlexADD.
Key Features:	Elastified
Remarks:	Addition of 25% by vol.



Mixing Ratio PreMix	4	C 2A44 Clear coat, fast drying
	1	A 2A44 Flex additive

2:1+10 % by volume



Mixing Ratio	100 % by volume	PreMix
---------------------	-----------------	--------



Hardener	50 % by volume	H 2A14 Topcoat hardener, fast H 2A24 Topcoat hardener, medium H 2A34 Topcoat hardener, slow
-----------------	----------------	---



Thinner	10 % by volume	R 2A14 Thinner, fast R 2A24 Thinner, medium R 2A34 Thinner, slow
----------------	----------------	--



Spray viscosity at 20°C	DIN 4: 18-21 s	Potlife at 20°C	4 h
	ISO 4: 40-55 s		

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

FastTOP

C 2A44

Variant with flex additive A 2A44 FlexADD

	 HVLP spray gun	 Compliant gravity-feed spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size	1.3	1.3-1.4
Number of spray coats		2
Film thickness	µm	50-60

Drying



Drying at 20°C 16 h

Drying at 60°C 45 min



Infrared (short wave) 8 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

