

UltraTOP

C 2A46

Variant with texture additive A 2A84 TextureADD

Application: Advance Series - Clear coat, performance C 2A46 UltraTOP with texture additive A 2A84 TextureADD.

Remarks: Add 25 to 50% of A 2A84 to produce the desired texture or mix as per mixing formula.



Mixing Ratio PreMix

2 C 2A46 Clear coat, performance
1 A 2A84 Texture additive

Or as per published formula.

2:1+10 % by volume



Mixing Ratio

100 % by volume PreMix



Hardener

50 % by volume H 2A24 Topcoat hardener, medium



Thinner

10 % by volume R 2A24 Thinner, medium



Spray viscosity at 20°C

DIN 4: 17-19 s

Potlife at 20°C

30 min

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



UltraTOP

C 2A46

Variant with texture additive A 2A84 TextureADD



HVLP spray gun



Compliant gravity-feed spray gun

Application pressure	2 bar
Nozzle size	1.2-1.3
Number of spray coats	2
Flash off at 20°C	Flash off until mat between spray coats and before stoving.
Film thickness	40-50 µm

Drying



Drying at 20°C	10 h
Drying at 40°C	30 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

