

GlossTOP

C 2A63

Clear coat, high gloss

Application:	Advance Series - Clear coat especially for ONYX HD basecoat.
Key Features:	Clear coat for high gloss finish.
Remarks:	Select hardener and thinner according to ambient temperature and size of object to be painted.

Solid Content	57 %
Density	0.9-1.05 g/cm ³
Storage temperature	5-45 °C

2:1+10 %



Mixing Ratio

100 % by volume C 2A63 Clear coat, high gloss



Hardener

50 % by volume
 H 2A14 Topcoat hardener, fast
 H 2A24 Topcoat hardener, medium
 H 2A34 Topcoat hardener, slow



Thinner

10 % by volume
 R 2A14 Thinner, fast
 R 2A24 Thinner, medium
 R 2A34 Thinner, slow



Spray viscosity at 20°C

DIN 4: 19-23 s **Potlife at 20°C** 2 h
 ISO 4: 45-60 s

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.



You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.





GlossTOP

C 2A63

Clear coat, high gloss

		 HVLP spray gun	 Compliant gravity-feed spray gun
Application pressure	bar	2	2
Nozzle pressure	bar	0.7	
Nozzle size		1.3-1.5	1.3-1.4
Number of spray coats		2	
Flash off at 20°C	min	3-5 min. intermediate flash-off between the spraycoats. No flash-off before drying.	
Film thickness	µm	40-60	
Application Remark		Alternatively: 1 ½ spray coats (no flash-off between coats required).	

Drying

	Drying at 20°C	10 h
	Drying at 60°C	30 min
	Infrared (short wave)	8 min

Drying Remark Drying times can be influenced by the selection of hardener, thinner and application. Additive A 2A14 SpeedADD can reduce drying times.

Remark Polishing after specified drying time and cooling.

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

GlossTOP

C 2A63

Clear coat, high gloss

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

