

CorrosionPROTECT

P 2A26

Wash primer

Application: Advance Series - undercoat solutions.
Key Features: Primer - for use as anti-corrosion primer on bare metal surfaces.

Storage temperature 5-45 °C
Shelf life 24 months



Cleaning

Clean the surface with UndercoatPREP before applying CorrosionPROTECT.

Handling



Product is suitable on

- Sheet steel
- Galvanised sheet steel
- Aluminium

Safety advice:

2004/42/IIIB(cIII)(780)760: The EU limit value for this product (product category: IIB.cIII) in ready-for-use form is max 780 grams of VOC per liter. The VOC content of this product is 760 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.





You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.





CorrosionPROTECT

P 2A26

Wash primer

		1:1+30%	
	Mixing Ratio	100 % by volume	P 2A26 Wash primer
	Hardener	100 % by volume	H 2A26 Wash primer hardener
	Thinner	30 % by volume	R 2A14 Thinner, fast R 2A24 Thinner, medium
	Spray viscosity at 20°C	DIN 4: 14-16 s ISO 4: 20-30 s	Potlife at 20°C 48 h

	 HVLP spray gun	 Compliant gravity-feed spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size	1.3-1.7	1.3-1.6
Number of spray coats		1-2
Film thickness	µm	10-15

Safety advice:

2004/42/IIIB(cIII)(780)760: The EU limit value for this product (product category: IIB.cIII) in ready-for-use form is max 780 grams of VOC per liter. The VOC content of this product is 760 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

CorrosionPROTECT

P 2A26

Wash primer

Drying



Drying at 20°C

10 min

Remark

Not recoatable with polyester body filler or waterborne products!

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

2004/42/IIIB(cIII)(780)760: The EU limit value for this product (product category: IIB.cIII) in ready-for-use form is max 780 grams of VOC per liter. The VOC content of this product is 760 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

