

BRIGHT Finish-R

C 2P62

eSense clear coat, superior gloss



Application:	Pioneer Series - eSense clear coat for R-M waterborne basecoats.
Key Features:	Eco effectiveness clear coat - high end gloss. For a superior finish.
Remarks:	Mix well and strain before application. Select hardener and thinner according to ambient temperature and size of object to be painted.

Solid Content	60 %
Density	0.95-1.1 g/cm ³
Storage temperature	5-45 °C
Shelf life	36 months

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.









BRIGHT Finish-R

C 2P62

eSense clear coat, superior gloss



	3:1:1	
	Mixing Ratio	300 % by volume C 2P62 eSense clear coat, superior gloss
	Hardener	100 % by volume H 2P15 eSense topcoat hardener, fast H 2P25 eSense topcoat hardener, medium H 2P35 eSense topcoat hardener, slow
	Thinner	100 % by volume R 2P15 eSense thinner, fast R 2P25 eSense thinner, medium R 2P35 eSense thinner, slow R 2P45 eSense thinner, extra slow
	Spray viscosity at 20°C	DIN 4: 18-22 s ISO 4: 40-55 s
	Potlife at 20°C	2 h

	 HVL spray gun	 Compliant gravity-feed spray gun
Application pressure	2 bar	2 bar
Nozzle pressure	0.7 bar	
Nozzle size	1.3	1.2-1.3
Number of spray coats	2	
Flash off at 20°C	3 - 5 min. intermediate flash off between the spray coats. No flash off before drying.	
Film thickness	40-60 µm	
Application Remark	Alternatively: 1 ½ spray coats (no flash off between coats required).	

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.





BRIGHT Finish-R

C 2P62

eSense clear coat, superior gloss



Drying

	Drying at 20°C	8 h
	Drying at 40°C	45-60 min
	Drying at 60°C	30 min
	Infrared (short wave)	10 min

Drying Remark Drying times can be influenced by the selection of hardener, thinner and application. FAST Tune-R additive can reduce drying times.

Remark Polishing after specified drying time and cooling.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

