

MULTI Purpos-R Grey



P 2P63

Variant for primer application for B 2P13 SPRAY Bodyfill-R.

Application: Pioneer Series - eSense undercoat solutions.

Key Features: eSense DTM, grey

Storage temperature 5-45 °C

Shelf life 24 months



Cleaning

Clean the surface with MULTI Clean-R before applying MULTI Purpos-R Grey.

Handling

Product is suitable on

- Sheet steel
- OEM parts with e-coat
- Old paintwork



PK 2P50 PRO Prep-R and P 2P63 MULTI Purpos-R Grey needed on bare

- Galvanised sheet steel
 - Aluminium
-

Safety advice:

2004/42/IIIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.









MULTI Purpos-R Grey



P 2P63

Variant for primer application for B 2P13 SPRAY Bodyfill-R.

		4:1:1	
	Mixing Ratio	100 % by volume	P 2P63 eSense DTM, grey
	Hardener	25 % by volume	H 2P60 eSense MULTI Purpos-R hardener
	Thinner	25 % by volume	R 2P20 eSense undercoat thinner, medium R 2P15 eSense thinner, fast R 2P25 eSense thinner, medium R 2P35 eSense thinner, slow
	Spray viscosity at 20°C	DIN 4: 15-20 s ISO 4: 25-50 s	Potlife at 20°C 90 min

	 HVLSP spray gun	 Compliant gravity-feed spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size	1.3	1.3-1.4
Number of spray coats		1
Film thickness	µm	15-25

Safety advice:

2004/42/IIIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



MULTI Purpos-R Grey

P 2P63

Variant for primer application for B 2P13 SPRAY Bodyfill-R.



Drying



Drying at 60°C

45 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

2004/42/IIIB(c I)(540)539: The EU limit value for this product (product category: IIB.c I) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

