

Technical Information

AIRFLASH A 2140



Additive for accelerating air drying

Product category: **C 5**

Fields of use:

Additive for accelerated air drying of R-M 2 component standard VOC clearcoats on vertical and horizontal surfaces.

AIRFLASH A 2140 is only intended for use with RAPIDCLEAR C 2570, EVERCLEAR C 2550 and GLOSSCLEAR C 2560.

Additional Information

Using AIRFLASH A 2140 will allow for a dust-free surface more quickly. Sandability, polishability and readiness for assembly will be significantly improved. AIRFLASH A 2140 is particularly suited for bodyshops who want to save energy and dry the clearcoat at a panel temperature below 60°C. AIRFLASH A 2140 can help to reduce the occupation times of the combi-booth and drying oven. AIRFLASH A 2140 is particularly suited for small repairs.

Technical characteristics

Solids content ~ 1.0%	Density 0.820 – 0.920 g/cm ³
Storage temperature min. 5°C to max. 45°C	Shelf life 12 months

Application

The additive replaces the thinner in the mixing ratio of the product in which it is used.

Substrates / Pre-treatment / Cleaning:

Refer to the technical data sheet of the product in which AIRFLASH A 2140 is used.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these statements do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 11/2016



AIRFLASH A 2140



	<p>R-M standard VOC clearcoat H 2550 AIRFLASH A 2140 Mix well and strain before application.</p>	<p>300% by vol. 100% by vol. 100% by vol.</p>																																									
<p>AIRFLASH A 2140 will reduce the potlife.</p>																																											
	<p>Refer to the technical data sheet of the product in which AIRFLASH A 2140 is used.</p>																																										
	<p>Spraycoats: 1 ½ Film thickness: approx. 50 µm</p>	<p>without intermediate flash-off time</p>																																									
	<table border="1"> <thead> <tr> <th></th> <th>20°C</th> <th>40°C</th> <th>60°C</th> </tr> </thead> <tbody> <tr> <td>RAPIDCLEAR C 2570</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Dust-free after</td> <td>20 – 30 min*</td> <td>10 – 15 min</td> <td>< 10 min</td> </tr> <tr> <td>Polishable after</td> <td>2 – 3 h</td> <td>1 h**</td> <td>1 h**</td> </tr> <tr> <td>EVERCLEAR C 2550</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Dust-free after</td> <td>25 – 35 min*</td> <td>15 – 20 min</td> <td>10 – 15 min</td> </tr> <tr> <td>Polishable after</td> <td>3 – 4 h</td> <td>1.5 h**</td> <td>1.5 h**</td> </tr> <tr> <td>GLOSSCLEAR C 2560</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Dust-free after</td> <td>35 – 45 min*</td> <td>20 – 25 min</td> <td>15 – 20 min</td> </tr> <tr> <td>Polishable after</td> <td>4 h</td> <td>2 h**</td> <td>2 h**</td> </tr> </tbody> </table>				20°C	40°C	60°C	RAPIDCLEAR C 2570				Dust-free after	20 – 30 min*	10 – 15 min	< 10 min	Polishable after	2 – 3 h	1 h**	1 h**	EVERCLEAR C 2550				Dust-free after	25 – 35 min*	15 – 20 min	10 – 15 min	Polishable after	3 – 4 h	1.5 h**	1.5 h**	GLOSSCLEAR C 2560				Dust-free after	35 – 45 min*	20 – 25 min	15 – 20 min	Polishable after	4 h	2 h**	2 h**
	20°C	40°C	60°C																																								
RAPIDCLEAR C 2570																																											
Dust-free after	20 – 30 min*	10 – 15 min	< 10 min																																								
Polishable after	2 – 3 h	1 h**	1 h**																																								
EVERCLEAR C 2550																																											
Dust-free after	25 – 35 min*	15 – 20 min	10 – 15 min																																								
Polishable after	3 – 4 h	1.5 h**	1.5 h**																																								
GLOSSCLEAR C 2560																																											
Dust-free after	35 – 45 min*	20 – 25 min	15 – 20 min																																								
Polishable after	4 h	2 h**	2 h**																																								
<p>*Spraybooth in circulating air mode **Waiting time at room temperature after surface drying in the oven</p>																																											

Finishing

Finishing operations can be performed after the indicated times.

Safety instructions

The products are suitable for professional use only.
It cannot be ruled out that this product contains particles < 0.1 µm.

Comply with present safety instructions and personal protective equipment.