


Technical Information

AM 880 PRIMEFILL



Primer filler

Product Category: **C 2.3**

Fields of use

Primer filler with anti-corrosive properties for direct use on metal substrates (steel, aluminum, galvanized steel as per quality standard of the automotive industry).

Additional Information

The product can be used either as a primer applied in one or two spraycoats followed by a filler coat or as primer filler directly under a topcoat.

Technical characteristics

Solids content 14 % ± 2	Density 0.700 – 0.800 g/cm ³
Storage temperature min. 5°C to max. 45°C	Shelf life 36 months

Application

Shake vigorously for 2 min. before use.

Substrate / Pre-treatment / Cleaning

Clean with PK 700 or PK 900.

Sand (steel with P80, aluminum with P150-P180, galvanized steel and old paintwork with P240). Clean with PK 1000.





The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.mmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 08/2019



Technical Information

AM 880 PRIMEFILL

	Do not use deformed aerosol cans. While shaking the can, do not strike against solid objects. During shaking, the mixing balls are released. Avoid bumps, friction and impact.		
		Primer	Primer filler
Spraycoats:		1 – 2	3 – 4
Film thickness:		15 – 20 µm	30 – 40 µm
	Drying at 20°C:	10 min.	1.5 – 2 hours
	Drying at 60°C:	/	30 min.
	(short wave)	/	5 min. at 50%
	(medium wave)	/	7 min.

Finishing

When product is used as a primer, apply an R-M 2K filler or an R-M topcoat wet on wet.

Intermediate sanding is required when flash-off time exceeds 10 hours at 20°C.

When product is used as primer filler, sand with P600 soft pad or wet with P800.

Safety instructions

2004/42/II B(e)(840)743: The EU limit value for this product (product category: IIB.e) in ready-for-use form is max 840 grams of VOC per liter. The VOC content of this product is 743 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.