

UV BLENDING Thinn- R





A 2P30

eSense UV blending additive

Application:	Pioneer Series - eSense UV Blending thinner
Key Features:	Smooths Pioneer Series - UV Finish-R transition areas by use of blending processes
Remarks:	The product is ready for use. Shake well before use.

Solid Content	11.3 %
Density	0.87 g/cm³
Storage temperature	15-40 °C

Ready for use

	 HVLP spray gun	 Compliant gravity-feed spray gun
Application pressure	bar	1-1.5
Nozzle size		1
Number of spray coats		2 - 3
Application Remark	Do not over apply. Allow a few seconds after application for melting and levelling before applying further material, if appearance is not as required.	

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.
The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



UV BLENDING Thinn- R



A 2P30

eSense UV blending additive

Drying



UV Curing

As recommended for the UV clear coat.

Drying Remark

Positioning and distance of lamp to painted surface is critical for required curing result

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

