

CHRONOTOP

C 1470

MS clear coat fast drying

Application: For small repairs (blend-in repairs, refinishing of one or two vertical panels). CHRONOTOP was designed for use on DIAMONT basecoats.

Remarks: Note: Use slow **BC 030** thinner in high temperatures or when air speed in booth is high.

Solid Content	42 % +/- 2
Density	0.92-1.02 g/cm ³
Storage temperature	5-45 °C
Shelf life	36 months



Mixing Ratio

100 Parts by volume C 1470 MS clear coat fast drying
(alternatively: 100 g)



Hardener

25 Parts by volume H 9000 Hardener, medium
(alternatively: 27 g)



Thinner

25-50 Parts by volume BC 020 THINNER
volume (alternatively: 23 - 45 g)



Spray viscosity at 20°C

DIN 4: 14-16 s **Potlife at 20°C** 4 h
ISO 4: 20-28 s

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.





CHRONOTOP

C 1470

MS clear coat fast drying

	 HVL P spray gun	 Compliant gravity-feed spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size	1.3	1.3-1.4
Number of spray coats		2
Film thickness	µm	50

Drying

	Drying at 20°C	2 h Ready to assemble after 2 h Dust-free after 20 min. Fully cured after 10 hours
	Drying at 60°C	15 min
	Infrared (short wave)	8 min

Remark Finishing operations after specified drying times and cooling.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.