


GHD CHASSISMIX

P 5433

GRAPHITE HD CHASSISMIX

Application:



construction machinery (steel), chassis painting, chassis (color change), container, steel and galvanized steel spare parts

Key Features:

- suitable for large areas / surfaces
- can be applied directly on steel or galvanized steel
- tintable
- good coverage of shot blasted profile
- brilliant top coat appearance
- improves the hiding power

Remarks:

Aluminum-Chassis have be primed with a suitable primer.
The substrate should be clean, free of dust, rust, oil and grease.

Substrates

- = Very well suited
- = well suited
- = suited in some cases

Steel	Galvanized steel	Stainless steel	Aluminium	Anodized Aluminium	GRP / SMC	PP-EPDM	R-M CV - Primer	R-M CV - Primer Filler / Filler	Powder coating	Coil-coating	Plywood	Wood	OEM-Paintwork	Old paint work
●●	●●	●			●		●		●	●			●	●

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIIB (c II)(540)530: The EU limit value for this product (product category: IIB(d) in ready to use form is max. 540 g/l. The VOC content of this product is 530 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



GHD CHASSISMIX

P 5433

GRAPHITE HD CHASSISMIX



Paint System

Spreading rate 540 m²/l at 1 µm

Solid Content 80 %



Pre Mix mix GHD CHASSISMIX (70 parts) with line GHD TOPCOAT (30 Parts)



Mixing Ratio 100:15 + 15 - 25% by volume



Hardener H 770, H 750, H 700



Thinner GV 200, GV 300, GV 400



Spray viscosity at 20°C DIN 4: 25-35 s

Potlife at 20°C 2 h

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIIB (c II)(540)530: The EU limit value for this product (product category: IIB(d) in ready to use form is max. 540 g/l. The VOC content of this product is 530 g/l.






The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.




GHD CHASSISMIX

P 5433

GRAPHITE HD CHASSISMIX

Application:		 Compliant - gravity feed cup	 HVLP spray gun	 Suction cup	 Airless/Airmix	 Pressure pot dbl.-pump
Application pressure	bar	2.2-2.5	2	2.5	2	2.5
Material pressure	bar				120-150	0.8-1.5
Nozzle size		1.6-1.8	1.7-1.9	1.7-1.9	0.28-0.33	1-1.1
Voltage	kV				50-80	
Elect. Resistance	Ω				700-1500	
Number of coats		2	2	2	1-2	2
Flash off at 20°C	min	10-15	10-15	10-15	10-15	10-15
Film thickness	µm	60-70				

	Drying	Overcoatable	Tack-free	Ready for masking	Ready to assemble	Sandable
		Min. Max.				
	Object Temp. 20°C	60 min 72 h				16 h
	Object Temp. 60°C	30 min				30 min

Remark

The shelf life of the mixed product (Line GHD TOPCOAT and GHD CHASSISMIX) is only 2 weeks. The corrosion protection can only be achieved, if the required film thickness is applied (covering of sand blasting roughness, edges). The adhesion on hot dipped galvanized steel has to be checked before.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIIB (c II)(540)530: The EU limit value for this product (product category: IIB(d) in ready to use form is max. 540 g/l. The VOC content of this product is 530 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



GHD CHASSISMIX

P 5433

GRAPHITE HD CHASSISMIX

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

2004/42/IIIB (c II)(540)530: The EU limit value for this product (product category: IIB(d) in ready to use form is max. 540 g/l. The VOC content of this product is 530 g/l.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

