

CHRONOTOP

C 1470

MS clear coat fast drying variant SPECIAL MAT 09

Application:	Matting agent which allows to reduce the gloss level of R-M solid-color topcoats and clears.
Key Features:	SPECIAL MAT 09 is compatible with all R-M clears and with the R-M topcoats UNO HD and UNO HD CP, UNO HD CP PLUS. SM 09 must not be used in mixing shelves.
Remarks:	Stir well before use. Option 1: When SPECIAL MAT 09 is contained in the mixing formula, possibly in combination with MT 900: Mix the components respecting the amounts specified in the mixing formula. Prepare the paint for application by adding hardener and thinner as indicated in the technical data sheet of the topcoat or clear being adjusted. Option 2: When matting an originally glossy topcoat / clear: Add SPECIAL MAT 09 to produce the desired degree of matting, up to a maximum of 70% by weight. Stir well. Then prepare the paint for application by adding hardener and thinner as indicated in the technical data sheet of the topcoat or clear being adjusted. Potlife: SPECIAL MAT 09 will reduce the potlife of the topcoat in which it is used.

Solid Content	42 % +/-2
Density	0.92-1.02 g/cm ³
Storage temperature	5-45 °C
Shelf life	36 months



Mixing Ratio PreMix

50 Parts by volume	C 1470 MS clear coat fast drying
50 Parts by volume	SM 09 Matting paste

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



CHRONOTOP

C 1470

MS clear coat fast drying variant SPECIAL MAT 09



Mixing Ratio 100 Parts by volume PreMix





Hardener 25 Parts by volume H 9000 Hardener, medium



Thinner 25-50 Parts by volume BC 020 THINNER



Spray viscosity at 20°C DIN 4: 14-16 s **Potlife at 20°C** 4 h
ISO 4: 20-28 s

	 HVLP spray gun	 Compliant gravity-feed spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size	1.3	1.3-1.4
Number of spray coats	2	
Flash off at 20°C	min IMPORTANT: Flash off until mat between coats and before force curing.	
Film thickness	µm	50

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



CHRONOTOP

C 1470

MS clear coat fast drying variant SPECIAL MAT 09

Drying



Drying at 20°C

2 h
Dust-free after 20 min.
Fully cured after 10 hours



Drying at 60°C

15 min

Infrared (short wave)

8 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm. The products are suitable for professional use only. For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

