DIAMONTOP CP

C 2410 Premium premix clear coat

Application:		For applications ranging from repair of individual panels to overall resprays. DIAMONTOP CP was designed for use on R-M waterborne basecoats.		
Remarks:		For combi-booths, take additional heating rate into account until panel temperature has been reached.		
		47 % +/- 2		
Density		0.94-1.04 g/cm ³		
Storage t	emperature	5-45 °C		
Shelf life		36 months		
		4:1		
	Mixing Ratio	100 Parts by volume C 2410 Premium premix clear coat (alternatively 100 g)		
Ê	Hardener	25 Parts by volume H 420 Hardener, medium (alternatively 27 g)		
	Spray viscosity at 20°C	DIN 4: 20-24 s Potlife at 20°C 2 h		
s ۲		ISO 4: 52-62 s		

Safety advice:

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < 0.1 μ m.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety

recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

page 1 of 2

12/2022



Technical Information

DIAMONTOP CP

C 2410 Premium premix clear coat

ure bar bar soats µm	0.7 1.3 On vertical surfaces, apply one thin and one (film thickness of 40-	full spraycoat without intermediate flash-off approx. 50 μm).
coats	1.3 On vertical surfaces, apply one thin and one (film thickness of	g full spraycoat without intermediate flash-off approx. 50 μm).
	2 On vertical surfaces, apply one thin and one (film thickness of	g full spraycoat without intermediate flash-off approx. 50 μm).
	On vertical surfaces, apply one thin and one (film thickness of	full spraycoat without intermediate flash-off approx. 50 μm).
μm	40-	
	40-60	
t 60°C	30 min	
(short wave)	8 min	
(medium	10-15 min	
	tt 60°C (short wave) (medium	(short wave) 8 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

2004/42/IIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready-for-use form is max 420 grams of VOC per liter. The VOC content of this product is 419 g/l.

It cannot be ruled out that this product contains particles < $0.1 \,\mu$ m.

The products are suitable for professional use only. For the use of this product please adhere to the actual safety

recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

page 2 of 2

12/2022

Perfection made simple