

EXTRASEALER WHITE

P 2420W 2K-Sealer

Application:	Two-component sealer that can be over coated wet on wet with any R-M topcoat. Particularly suitable for use on new panels.
Key Features:	EXTRASEALER WHITE can be mixed with 5% UNO HD CP / UNO HD CP PLUS mixing bases or 5% ONYX HD mixing bases.
Remarks:	Stir well before use.

Solid Content	73 % +/- 2
Density	1.41-1.51 g/cm ³
Storage temperature	5-45 °C
Shelf life	24 months



Cleaning

Clean with PK 700 or PK 900.
Sand (steel with P80, aluminum with P150-P180, galvanized steel and solvent-resistant old paintwork with P320).
Clean with PK 1000.
No need to sand new e-coated parts.
Prime rather large bare metal areas with EUROFILL before filler application.

Safety advice:

2004/42/IIIB(Cl)(540)539: The EU limit value for this product (product category: IIB.Cl) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

EXTRASEALER WHITE

P 2420W 2K-Sealer



Mixing Ratio

300 Parts by volume P 2420W 2K-Sealer
(alternatively: 100 g)



Hardener

100 Parts by volume D 70 Undercoat hardener, fast
D 80 Undercoat hardener, medium
(alternatively: 23 g)



Thinner

100 Parts by volume FR 500 THINNER
R 2200 Thinner, medium
R 2300 Thinner, slow
(alternatively: 21 g)



Spray viscosity at 20°C

DIN 4: 17-19 s
ISO 4: 35-45 s

Potlife at 20°C

2 h



HVLP spray gun



Compliant gravity-feed spray gun

		HVLP spray gun	Compliant gravity-feed spray gun
Application pressure	bar		2-2.5
Nozzle pressure	bar	0.7	
Nozzle size		1.3-1.5	1.3-1.4
Number of spray coats			1
Flash off at 20°C	min		15
Film thickness	µm		20-35

Remark

Apply R-M topcoat wet on wet.

Parts coated with EXTRASEALER WHITE can be over coated without intermediate sanding for up to 5 days.

Safety advice:

2004/42/IIIB(cI)(540)539: The EU limit value for this product (product category: IIB.cI) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



EXTRASEALER WHITE

P 2420W 2K-Sealer

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

2004/42/IIIB(Cl)(540)539: The EU limit value for this product (product category: IIB.cl) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

