

Product code: AU04-9006

GRAPHITE HD CV 12, direct-gloss, metallic, white aluminium

	Resin base		Modified polyaci	vlate			
	Troom Buoc		Modified polyaci	ylate			
	Mixing ratio		100:25:25 by volume, use mixing stick				
	Hardener		H 350 normal H 300 fast				
圣	Reducer		GV 100				
S	Spray viscosity Potlife		18 - 22 s DIN 4 1,5 h				
	Application		Number of spraycoats	Spraying pressure	Material pressure	Nozzle diameter	Compliant gun
	Double membrane p Pressure pot	oump	1.5	2,5 bar	0.9 – 1.5 bar	1.1 mm	1.0 mm
**	Gravity-feed spraygun		1.5	2.5 bar	-	1.3 mm	1.3 mm
*	Suction-feed spraygun		1.5	2.5 bar	-	1.7 mm	1.6 mm
	Dry film thickness Spreading rate (DIN 53 219)		40 – 60 μm 536 m²/l at 1 μm film thickness				
	Solids content (DIN EN ISO 3251)		60% by weight \pm 4 (62% \pm 4 at original viscosity)				
) _† / _† /	Flash-off at	20°C	10 – 15 min.				
	Drying		Recoatable	Tack-	ree Tar	eable	Ready for assembly
	Panel temperature	20°C	16 h	2.5	h 1	6 h	12 h
		60°C	30 min.	0 min. after cooling		cooling	after cooling
	Substrates		All R-M CV primer fillers and surfacers; sanded old paintwork.				
	Remarks		Application: Pre-spray 1 thin grip coat with the finishing coat following immediately. Alternatively: apply several thin spray coats. Air drying → up to 16 h recoatable with itself without sanding, after oven and 16 h air drying use an adhesion promoter for multi colour process. Ambient processing temperature should be at least 18° C!				



2004/42/IIB(d)

(420)419

Please refer to the EU Material Safety Data Sheet for product labelling as required by Directive 1999/45/EC and the respective national rules. The products are suitable for professional use only.

The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. It cannot be ruled out that this product contains particles < 0.1 µm.

R-M Automotive Paint F-60676 Clermont de l'Oise Cedex

Tel. (33) (0) 3 44 77 77 77

www.rmpaint.com

Feb. 2010