


## TRANSPARENT SEALER CP

	Resin base		Two-pack PU acrylic				
	Mixing ratio		100 : 50 + 30 %				
B	Hardener		H 360 H 310				
Z	Reducer		GV200 GV100				
∏s	Spray viscosity Potlife		17 s DIN 4 2 h				
	Application		Number of spraycoats	Spraying pressure	Material pressure	Nozzle diameter	Compliant gun
	Double membrane p Pressure pot	oump	-	-	-	-	
	Airless/Airmix		-	-	-	-	
»» <del> </del>	Gravity-feed spraygun		1	2,5 bar	-	1.5 mm	1.4 mm
***************************************	Suction-feed spraygun		1	2,5 bar		1.7 mm	1.6 mm
	Dry film thickness Spreading rate (DIN	53 219)	20 - 25 μm 404 m²/l at 1 μm film thickness				
	Solids content (DIN EN ISO 3251)		52% by weight $\pm$ 4 (64 $\pm$ 4% at original viscosity)				
<u>}†}†</u>	Flash-off at	20°C	15 min. – <b>max.</b>	2 h			
	Drying		Recoatable	Tack-fre	ee Ta	peable	Ready for assembly
	Panel temperature	20°C	15 min.				
		60°C					
	Substrates (Pre-treated) old paintwork						
	Remarks		Tinting with up to 10 % GRAPHITE HD Mixing Bases possible				



2004/42/IIB(cII)

(540)525

Please refer to the EU Material Safety Data Sheet for product labelling as required by Directive 1999/45/EC and the respective national rules. The products are suitable for professional use only.

The EU limit value for this product (product category: IIB.cII) in ready to use form is max 540 g/litre of VOC. The VOC content of this product is 525 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. It cannot be ruled out that this product contains particles < 0.1 µm.

R-M Automotive Paint F-60676 Clermont de l'Oise Cedex

Tel. (33) (0) 3 44 77 77 77

www.rmpaint.com

Feb. 2010