

MULTI SPOT

A 2550

Blending thinner

Application: Blending thinner designed to melt in fade-out areas of UNO HD CP / UNO HD CP PLUS and R-M clears in blend-in repairs.

Key Features: MULTI SPOT reduces polishing time and promotes better leveling of the clearcoat in the blending areas.

| | |
|----------------------------|-----------------------------|
| Solid Content | 4 % +/-2 |
| Density | 0.83-0.93 g/cm ³ |
| Storage temperature | 5-45 °C |
| Shelf life | 36 months |



Mixing Ratio 100 Parts by volume A 2550 Blending thinner



Hardener 2 Parts by volume H 9000 Hardener, medium (Untinted version)



Spray viscosity at 20°C DIN 4: 12-13 s **Potlife at 20°C** 1 h
ISO 4: 15-17 s

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



MULTI SPOT

A 2550

Blending thinner

| |  HVL P spray gun |  Compliant gravity-feed spray gun |
|-----------------------|---------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------|
| Application pressure | bar | 1-1.5 |
| Nozzle pressure | bar | 0.7 |
| Nozzle size | | 1-1.2 |
| Number of spray coats | | 2-3 |
| Film thickness | µm | 10 |
| Application Remark | | Mini spray gun |

Drying



Drying at 60°C 30 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

