

## PRIMEFLASH A 2100



Air drying accelerator primerfillers

Product category: **C 5**

### Fields of use:

Additive for accelerated air drying of R-M 2 component standard primerfiller on vertical and horizontal surfaces.

PRIMEFLASH A 2100 is only intended for use with PERFECTFILLER WHITE / GREY / BLACK

### Additional Information

Using PRIMEFLASH A 2100 will allow for a dust-free surface more quickly. Sandability and readiness for assembly will be significantly improved. PRIMEFLASH A 2100 is particularly suited for bodyshops who want to save energy and dry the primerfiller at a room temperature of 20°C. PRIMEFLASH A 2100 can help to reduce the occupation times of the combi-booth and drying oven. PRIMEFLASH A 2100 is particularly suited for small repairs.

### Technical characteristics

Solids content ~ 1.0%	Density 0.820 – 0.920 g/cm <sup>3</sup>
Storage temperature min. 5°C to max. 45°C	Shelf life 36 months

### Application

The additive replaces the thinner in the mixing ratio of the product in which it is used.

### Substrates / Pre-treatment / Cleaning:





Refer to the technical data sheet of the product in which PRIMEFLASH A 2100 is used.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these statements do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 11/2017



## PRIMEFLASH A 2100

	<b>PERFECTFILLER WHITE / GREY / BLACK</b> <b>D 70 / D 80</b> <b>PRIMEFLASH A 2100</b> Mix well and strain before application.	100% by vol. 25% by vol. 25% by vol.
	PRIMEFLASH A 2100 will reduce the potlife.	
	Refer to the technical data sheet of the product in which PRIMEFLASH A 2100 is used.	
	Spraycoats: 2 Film thickness: 50 – 70 µm	
	Drying at 20°C	approx. 40 min.

### Finishing

	Dry with P400 – P500
---	----------------------

### Safety instructions

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

Comply with present safety instructions and personal protective equipment.