


Technical Information

PROFILLER GREY



2K Primerfiller – high build version

Product Category: **C 2.3**

Fields of use

PROFILLER GREY version for repairs in which high build is required

Additional Information

Technical characteristics

Solids content 76 % ± 2	Density 1.670 –1.770 g/cm ³
Storage temperature min. 5°C to max. 45°C	Shelf life 24 months

Application

Stir well before use.

Flash-off between spraycoats until mat, no flash-off before drying.

Substrate / Pre-treatment / Cleaning

Clean with PK 700 or PK 900.

Sand (steel with P80, aluminum with P150-P180, galvanized steel and solvent-resistant old paintwork with P240).

Clean with PK 1000.


Prime rather large bare metal areas with EUROFILL before filler application.






The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.mppaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 10/2015





PROFILLER GREY



	PROFILLER GREY D 70 / D 80 FR 500 / R 2100 / R 2200 / R 2300	100% by vol. 25% by vol. 25% by vol.	100 g 14 g 13 g
	Viscosity at 20°C: ISO 4 cup: DIN 4 cup:	50 to 65 seconds 20 to 24 seconds	
	Potlife: 1 hour at 20°C		
	HVLP gravity-feed spraygun Compliant gravity-feed spraygun	1.7 – 1.9 mm 1.6 – 1.8 mm	0.7 bar at the nozzle 2.0 – 2.5 bar
	Number of spraycoats: Film thickness:	3 – 4 µm 100 – 200 µm	
	Drying at < 20°C: Drying at 60°C:	over Night 40 min.	

Finishing

	Dry with P400
	Wet with P800

Safety instructions

2004/42/IIIB(cII)(540)539: The EU limit value for this product (product category: IIB.cII) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.