

# PERFECTFILLER WHITE

## P 2430W

### Variant with PRIMEFLASH

<b>Application:</b>	2-component filler based on polyurethane. Very reliable in application; short drying times and very good sanding behavior.
<b>Remarks:</b>	Stir well before use. Using PRIMEFLASH A 2100 will allow for a dust-free surface more quickly. Sandability and readiness for assembly will be significantly improved. PRIMEFLASH A 2100 is particularly suited for bodyshops who want to save energy and dry the primerfiller at a room temperature of 20°C. PRIMEFLASH A 2100 can help to reduce the occupation times of the combibooth and drying oven. PRIMEFLASH A 2100 is particularly suited for small repairs. PRIMEFLASH A 2100 will reduce the potlife.

---

<b>Solid Content</b>	77 % +/- 2
<b>Density</b>	1.69-1.79 g/cm <sup>3</sup>
<b>Storage temperature</b>	5-45 °C
<b>Shelf life</b>	24 months

---



#### Cleaning

Clean with PK 700 or PK 900.  
Sand (steel with P80, aluminum with P150-P180, galvanized steel and solvent-resistant old paintwork with P240).  
Clean with PK 1000.  
Prime rather large bare metal areas with EUROFILL before filler application.

---

#### Safety advice:

**2004/42/IIIB(cII)(540)539:** The EU limit value for this product (product category: IIB.cII) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# PERFECTFILLER WHITE

**P 2430W**

Variant with PRIMEFLASH

Mix well and strain before application.



**Mixing Ratio**

100 Parts by volume P 2430W 2K Fast Dry Surfacer



**Hardener**

25 Parts by volume D 70 Undercoat hardener, fast  
D 80 Undercoat hardener, medium





**Thinner**

25 Parts by volume A 2100 Air drying accelerator primerfillers



**Spray viscosity at 20°C**

DIN 4: 18-23 s **Potlife at 20°C**  
ISO 4: 40-58 s

	 <b>HVLP spray gun</b>	 <b>Compliant gravity-feed spray gun</b>
<b>Application pressure</b>	bar	2-2.5
<b>Nozzle pressure</b>	bar	0.7
<b>Nozzle size</b>	1.7-1.9	1.6-1.8
<b>Number of spray coats</b>	2	
<b>Flash off at 20°C</b>	min	Flash-off between spraycoats until mat, no flash-off before drying.
<b>Film thickness</b>	µm	50-70

**Safety advice:**

**2004/42/IIIB(cII)(540)539:** The EU limit value for this product (product category: IIB.cII) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



# PERFECTFILLER WHITE

**P 2430W**

Variant with PRIMEFLASH

## Drying



Drying at 20°C      40 min



Orbital sanding, dry

P400 – P500

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

### Safety advice:

**2004/42/IIIB(cII)(540)539:** The EU limit value for this product (product category: IIB.cII) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions.

You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.