

# PROFILLER BLACK

**P 2435B**

**Variant with JET 5**

**Application:** 2-component filler based on polyurethane. Very reliable in application and very good sanding behavior.

**Remarks:** Stir well before use.  
Important: The addition of JET 5 will reduce the potlife of the product.  
Use a fast thinner when working in low temperatures (approx. 12°C).  
1% of JET 5 = 1 capful of JET 5 per liter of ready-for-use product (base + hardener + thinner).  
JET 5 should always be used in small amounts (4 % max.). If you add too much JET 5, you will risk loss of gloss.

---

<b>Solid Content</b>	73 % +/- 2
<b>Density</b>	1.67-1.77 g/cm <sup>3</sup>
<b>Storage temperature</b>	5-45 °C
<b>Shelf life</b>	24 months

---



## Cleaning

Clean with PK 700 or PK 900  
Sand (steel with P80, aluminum with P150-P180, galvanized steel and solvent-resistant old paintwork with P240).  
Clean with PK 1000.  
Prime rather large bare metal areas with EUROFILL before filler application.

---

## Safety advice:

2004/42/IIIB(cII)(540)539: The EU limit value for this product (product category: IIB.cII) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



# PROFILLER BLACK

**P 2435B**

Variant with JET 5



**Mixing Ratio**

100 Parts by vol P 2435B 2K Primerfiller



**Hardener**

25 Parts by vol D 70 Undercoat hardener, fast  
D 80 Undercoat hardener, medium



**Thinner**

25 Parts by vol FR 500 THINNER  
R 2100 Thinner, fast  
R 2200 Thinner, medium  
R 2300 Thinner, slow

**Additiv**

1-4 Parts by vol

A 2150 Drying accelerator  
The normal application temperature for paint products is 20°C. If the application temperature is lower, the following percentages apply:

- 12°C - 15°C: 2 %
- 18°C: 1 %



**Spray viscosity at 20°C**

DIN 4: 20-24 s  
ISO 4: 50-65 s

**Potlife at 20°C** 30 min

**Safety advice:**

2004/42/IIIB(cII)(540)539: The EU limit value for this product (product category: IIB.cII) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.



The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.



# PROFILLER BLACK

**P 2435B**

Variant with JET 5

	 HVL spray gun	 Compliant gravity-feed spray gun
Application pressure	bar	2-2.5
Nozzle pressure	bar	0.7
Nozzle size	1.7-1.9	1.6-1.8
Number of spray coats		2
Flash off at 20°C	min	Flash-off between spraycoats until mat, no flash-off before drying.
Film thickness	µm	50-70

## Drying



Drying at 20°C 1.5 h

Drying at 60°C 20 min



Infrared (short wave) 6 min



Sanding manual, wet

P 800



Orbital sanding, dry

P 400

## Safety advice:

2004/42/IIIB(cII)(540)539: The EU limit value for this product (product category: IIB.cII) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

# PROFILLER BLACK

**P 2435B**

**Variant with JET 5**

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

---

**Safety advice:**

2004/42/II B(cII)(540)539: The EU limit value for this product (product category: IIB.cII) in ready-for-use form is max 540 grams of VOC per liter. The VOC content of this product is 539 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.rmpaint.com](http://www.rmpaint.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

