

SEALERPLAST 80

P 2440

Adhesion primer for plastics

Application: SEALER PLAST 80 is an adhesion primer for plastics.

Key Features: It ensures good adhesion of the following coats (filler, topcoat).

Remarks: Stir well before use. SEALERPLAST 80 is ready for use.
Important: thermoplastic finishes must be removed.
Potlife: Unlimited in sealed container

Solid Content 7 % +/- 2

Storage temperature 5-45 °C

Shelf life 24 months



Cleaning

Important: thermoplastic finishes must be removed.



Spray viscosity at 20°C DIN 4: 13 s **Potlife at 20°C**
ISO 4: 14 s

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.
The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.
The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

SEALERPLAST 80

P 2440

Adhesion primer for plastics



HVLP spray gun



Compliant gravity-feed spray gun

		HVLP spray gun	Compliant gravity-feed spray gun
Application pressure	bar		2
Nozzle pressure	bar	0.7	
Nozzle size		1.3	1.3-1.4
Number of spray coats			1 - 2
Flash off at 20°C	min		15
Film thickness	µm		10 approx.

Remark Apply R-M 2K PU filler wet on wet. Apply SEALERPLAST 80 again when the flash-off time exceeds 30 min at 20°C.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.rmpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

