

Polyester finishing putty

Product Category: **C 2.1**

Fields of use

Fine polyester putty to be used for closing pores and leveling out irregularities before filler application in small damage repairs. Suitable for direct application to the substrates commonly used in the automotive industry – steel, galvanized steel, aluminum and glass-fiber reinforced plastics (GRP, SMC).

Additional Information

Technical characteristics

Solids content 86 % ± 2	Density 1.480–1.580 g/cm ³
Storage temperature min. 5°C up to max. 45°C	Shelf life 12 months

Application

Stir well before use. Mix intensively to avoid any marble effect.
Respect the mixing ratio. Using too much hardener can lead to topcoat discoloration (peroxide spots) while using too little hardener can increase the drying time.

Substrate / Pre-treatment / Cleaning

Clean with PK 700 or PK 900.
Sand (steel and galvanized steel with P80, aluminum with P150-P180).
Clean with PK 1000.


Do not use the product on phosphating primers or thermoplastic substrates.






The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.mpaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 12/2014



STOP EXTRA FIN



	Temperature	< 12°C	12 – 25°C	> 25°C
	STOP EXTRA FIN	100 g	100 g	100 g
	Hardener	3 g	2.5 g	1.5 g
Potlife: 5 minutes at 20°C				
	Number of coats	2		
	Drying at 20°C: Drying at 60°C: Drying will take longer when product is applied to a cold substrate.	20 min. 10 min.		
	(short wave) (medium wave)	4 min. at 50% 6 min.		
	Dry with P150, P240. Note: no wet sanding!			

Finishing

Safety instructions

2004/42/IIB(b)(250)180: The EU limit value for this product (product category: IIB.b) in ready-for-use form is max 250 grams of VOC per liter. The VOC content of this product is 180 g/l.

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.