

PREP'ART

New panel with cathodic electro-coat (OEM primer)

A 1.1

Process description

PREP'ART is a system of 6 matching processes for refinishing all substrates commonly encountered in automotive coating operations.

These processes have been developed in order to enable professional refinishers to maintain the quality standards of high-grade automotive finishes with outstanding efficiency.

Substrates

- Cathodic e-coat (OEM primer)

Products required

- PK 700, PK 1000
- EXTRASEALER WHITE / BLACK
- R-M topcoat

Safety instructions

It cannot be ruled out that these products contain particles < 0.1 µm.




The products are suitable for professional use only.

For the use of these products please adhere to the actual safety recommendations and the personal protective equipment.


Pre-treatment

| | |
|---|------------------------------|
|  | Degreasing PK 700 or PK 1000 |
|---|------------------------------|

Filler

| | | |
|---|--|--|
|  | EXTRASEALER WHITE / BLACK D 70 / D 80 FR 500 / R 2200 / R 2300 | 300% by vol. 100% by vol. 100% by vol. |
|  | Spraycoats: Film thickness: | 1 20 – 35 µm |
|  | Flash-off time at 20°C | 15 min. |

Topcoat

| | |
|---|---|
|  | ONYX HD, UNO HD CP, UNO HD CP PLUS Apply in accordance with the Technical Data Sheet |
|---|---|

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.mppaint.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

R-M Automotive Refinish Paints, Z.I. du Merret F-60676 Clermont de l'Oise Cedex, Tel. (+33) (0) 3 44 77 77 77, 11/2017