

EpoxyPROTECT Grey

P 2A23

Variant Wet-on-Wet Filler for metal

Application:	Advance Series - undercoat solutions.
Key Features:	Corrosion protection.
Remarks:	Minimum temperature for air drying: +59°F (15°C). Storage Temperature: 41-113 °F (5-45 °C) Shelf Life: 36 months

Handling

Product is suitable on



- Sheet steel
- Galvanised sheet steel
- Aluminium
- OEM parts with e-coat
- Old paintwork

VOC ready for use	459 g/l	3.8 lb/gal
--------------------------	---------	------------

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.





Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Material Safety Data Sheet (MSDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.





EpoxyPROTECT Grey

P 2A23

Variant Wet-on-Wet Filler for metal

		4:1:1	
	Mixing Ratio	100 % by volume	P 2A23 Primer filler, grey
	Hardener	25 % by volume	H 2A23 Epoxy hardener
	Thinner	25 % by volume	R 2A24 Thinner, medium
	Spray viscosity at 68°F / 20°C	DIN 4: 18-20 s ISO 4: 40-50 s	
	Potlife at 68°F / 20°C	8 h	

	 HVLP spray gun	 Compliant gravity-feed spray gun
Application pressure		29 psi
Nozzle pressure	10.2 psi	
Nozzle size	1.3	1.3-1.4
Number of spraycoats		½ + 1
Flash-off at 68°F / 20°C		20 min
Film thickness		1-1.4 mil

Remark Intermediate sanding is required when flash off time exceeds 5 hours at 68°F (20°C).

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Material Safety Data Sheet (MSDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.



EpoxyPROTECT Grey

P 2A23

Variant Wet-on-Wet Filler for metal

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Material Safety Data Sheet (MSDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

