

MULTI Purpos-R Black



eSense
repair the right way

P 2P65

Variant for sanding filler (paintable plastics)

Application: Pioneer Series - eSense undercoat solutions.

Key Features: eSense DTM, black

Remarks: MULTI Purpos-R Black can be mixed with MULTI Purpos-R White to achieve different grey shades.

Storage Temperature: 41-113 °F (5-45 °C)
Shelf Life: 24 months



Cleaning

Clean the surface with MULTI Clean-R before applying MULTI Purpos-R Black.

Handling



Use on plastic substrates in combination with A 2P40 PLASTIC Tune-R.

Product is suitable on

Pur-RIM / PP-EPDM / ABS / GRP-SMC / PC-PBTP / PA / PPO / rigid PVC /
Sheet steel / Galvanised sheet steel / Aluminium / OEM parts with e-coat / Old paintwork

VOC ready for use 539 g/l 4.5 lb/gal

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Material Safety Data Sheet (MSDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.







MULTI Purpos-R Black





eSense
repair the right way

P 2P65

Variant for sanding filler (paintable plastics)

| | | |
|---|---------------------------------------|--|
| | 5:1:1 | |
|  | Mixing Ratio | 100 % by volume P 2P65 eSense DTM, black |
|  | Hardener | 20 % by volume H 2P60 eSense MULTI Purpos-R hardener |
|  | Thinner | 20 % by volume A 2P40 eSense plastic adhesion additive |
|  | Spray viscosity at 68°F / 20°C | DIN 4: 18-20 s ISO 4: 40-50 s |
| | Potlife at 68°F / 20°C | 90 min |

| |  HVLP spray gun |  Compliant gravity-feed spray gun |
|---------------------------------|---|--|
| Application pressure | | 29 psi |
| Nozzle pressure | 10.2 psi | |
| Nozzle size | 1.7-1.9 | 1.6-1.8 |
| Number of spraycoats | $\frac{1}{2} + 1$ | |
| Flash-off at 68°F / 20°C | Flash off between spray coats until mat, no flash off before drying. | |
| Film thickness | 2-2.8 mil | |

Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Material Safety Data Sheet (MSDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.



MULTI Purpos-R Black



eSense
repair the right way

P 2P65

Variant for sanding filler (paintable plastics)

Drying



Drying at 68°F / 20°C 16 h

Drying at 140°F / 60°C 35 min



Infrared (short wave) 9 min



Orbital sanding, dry

P400 - P600

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Material Safety Data Sheet (MSDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

