

# WET Fill-R White

P 2P71

Variant Wet-on-Wet Filler with A 2P17 FAST Tune-R for metal



<b>Application:</b>	Pioneer Series - eSense undercoat solutions.
<b>Key Features:</b>	Reduction of flash off times. No need to sand new e-coated parts.
<b>Remarks:</b>	Can be mixed with WET Fill-R Black at any ratio to produce different shades of grey. Storage Temperature: 41-113 °F (5-45 °C) Shelf Life: 24 months

## Handling

### Product is suitable on

- OEM parts with e-coat
- Old paintwork
- GRP / SMC



### If bare metal areas are primed, the product can be used on

- Sheet steel
- Galvanised sheet steel
- Aluminium

<b>VOC ready for use</b>	539 g/l	4.5 lb/gal
--------------------------	---------	------------

## Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Material Safety Data Sheet (MSDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.









# WET Fill-R White

**P 2P71**

**Variant Wet-on-Wet Filler with A 2P17 FAST Tune-R for metal**



		<b>3:1:1</b>	
	<b>Mixing Ratio</b>	100 % by volume	P 2P71 eSense wet-on-wet filler, white
	<b>Hardener</b>	33 % by volume	H 2P84 eSense Fill-R hardener
	<b>Thinner</b>	33 % by volume	A 2P17 eSense speed additive
	<b>Spray viscosity at 68°F / 20°C</b>	DIN 4: 17-19 s ISO 4: 35-45 s	
	<b>Potlife at 68°F / 20°C</b>	30 min	

	 <b>HVLP spray gun</b>	 <b>Compliant gravity-feed spray gun</b>
<b>Application pressure</b>		29 psi
<b>Nozzle pressure</b>	10.2 psi	
<b>Nozzle size</b>	1.3-1.4	1.3-1.4
<b>Number of spraycoats</b>	1-2 (one on body-filled area and one on entire surface to be painted)	
<b>Flash-off at 68°F / 20°C</b>	10 min	
<b>Film thickness</b>	0.8-1.4 mil	

**Safety advice:**

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Material Safety Data Sheet (MSDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.



# WET Fill-R White

P 2P71

Variant Wet-on-Wet Filler with A 2P17 FAST Tune-R for metal



## Drying

**Drying Remark** If the recommended drying time is exceeded by more than 20 min, the panel has to be lightly scuffsanded.

**Remark** Apply topcoat wet on wet.

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



## Safety advice:

It cannot be ruled out that this product contains particles < 0.1 µm.

The products are suitable for professional use only.

For the use of this product please adhere to the actual safety recommendations and the personal protective equipment.

Materials described are for application by professional trained personnel only using proper equipment. Products may be hazardous and should be used according to label directions and technical data information. Appropriate respiratory protection should be worn at all times while products are in use - read product label and Material Safety Data Sheet (MSDS) for specific details. Statements and methods described are based upon the latest standard of technology known to the manufacturer. Application procedures cited are suggestions only and are not to be interpreted as warranty for events resulting from their use. Dilution ratios are intended to provide maximum performance within the typical Volatile Organic Compound (VOC) restriction for product use. Specific VOC limits need to be referenced to verify local compliance. Altering the solvent or dilution ratio may impact VOC compliance. User is solely responsible to ensure product use and application is in accordance with all applicable regulatory, legislative, and municipal requirements.

